Ciech Vitrosilicon	TECHNOLOGICAL DOCUMENTATION	Edition	Copy number	11	
		Date of issue		22.01.2018	
		Prepared by		Paweł Sieraszewski	
		Approved by		Dobiesław Szeszo	

PRODUCT SPECIFICATION

VITROLIQ·P	Name of the process: **VITROLIQ P – 40** (Previously name: R-40) Potassium silicates water solution	Number of process : **5** Index **ZI/P-5/R-40**

1. Product properties

a) Apperance:

Clear or opalescent liquid

b) Chemical properties

Water solution of potassium silicates with following parameters:

- Molar ratio 3,00 – 3,40
- Weight ratio 1,91 – 2,17
- Density (at 20°C) 1,38 – 1,42 g/cm^3
- Viscosity (at 20^{o}C) min 210 cP
- Oxides min 36% w/w

Valid with polish version only